

Technical Specification References

Classification	Specification	Designation of Grade	Mechanical Properties			Chemical Composition %					Bend Test (N2)		Flattening Test H
			Tensile Strength Min.	Yield Strength Min.	Elongation Min.	C	Si	Mn	P	S	Bending Angle	Bending Radius	
			N/mm ²	N/mm ²	%	Max	Max	Max	Max	Max			
Welded Steel Tubes - Light, Medium & Heavy	BS EN 10255 : 2004	-	320 to 520	195	20 (N3)	0.20	-	1.20	0.045	0.045	180°	6D	3/5 D
Carbon Steel Pipes For Ordinary Piping	JIS G 3452	SGP	290min.	-	(N1) Test Piece No. 11 & 12 - 30min. (N1) Test Piece No. 5 - 25min.	-	-	-	0.040	0.040	90°	6D	2/3 D
ASTM Standard Welded Steel Pipes	ASTM A53	Grade A	330min.	205min.	As specified in A-53 specification	0.25	-	0.95	0.050	0.060	90°	12D	1/3 D
		Grade B	415min.	240min.		0.30	-	1.20	0.050	0.060			
ERW Steel Tubes for Cement Lined Pipes	BS 3601	ERW 320	320 - 460	195 min.	25 (N3)	0.16	-	0.30 - 0.70	0.040	0.040	-	-	As specified in BS 3601 Specification
		ERW 430	430 - 570	275 min.	22 (N3)	0.21	0.35	0.40 - 1.20	0.040	0.040			
Alpine Manufacturer Standard Welded Steel Pipes	APM S 002	(A) (AA)	270min.	170min.	20 (N3)	0.20	-	1.20	0.045	0.045	90°	6D	1/3 D

NOTES : (N1) - When the tensile test is carried out on No. 12 or No. 15 test piece for the pipe under 8mm in wall thickness the minimum value of elongation shall be obtained by subtracting 1.5% from the thickness values of elongation given in Table above for each 1mm decrease in wall thickness, and rounding off to an integer in accordance with JIS Z 8401

(N1) - The values of elongation given in Table above shall not applied to the pipe whose nominal size is 32mm or smaller

(N2) - Bend test in table above only applied to pipes of nominal size 2" (50mm) or smaller.

(N3) Gauge length $L_0 = 5.65 \sqrt{S_0}$ (%)

H - Distance between the plates

D - Outside diameter of the pipe

APM S 002 - Manufacturer Standard

Carbon Steel Pipes For Ordinary Piping

JIS G 3452 - SGP

Nominal Size		Outside Diameter			Wall Thickness	Calculated Weight Plain Ends		Test Pressure	
in	mm	mm	Max. (mm)	Min. (mm)	mm	kg/m	lb/ft	kg/cm ²	PSI
1/2	15	21.7	22.2	21.2	2.8	1.31	0.880	25	360
3/4	20	27.2	27.7	26.7	2.8	1.68	1.13	25	360
1	25	34.0	34.5	33.5	3.2	2.43	1.63	25	360
1 1/4	32	42.7	43.2	42.2	3.5	3.38	2.27	25	360
1 1/2	40	48.6	49.1	48.1	3.5	3.89	2.61	25	360
2	50	60.5	61.1	59.9	3.8	5.31	3.57	25	360
2 1/2	65	76.3	77.1	75.5	4.2	7.47	5.02	25	360
3	80	89.1	90.0	88.2	4.2	8.79	5.91	25	360
3 1/2	90	101.6	102.6	100.6	4.2	10.1	6.79	25	360
4	100	114.3	115.4	113.2	4.5	12.2	8.20	25	360
5	125	139.8	141.2	138.4	4.5	15.0	10.1	25	360
6	150	165.2	166.8	163.6	5.0	19.8	13.3	25	360
7	175	190.7	192.3	189.1	5.3	24.2	16.3	25	360
8	200	216.3	218.0	214.6	5.8	30.1	20.2	25	360
10	250	267.4	269.5	265.3	6.6	42.4	28.5	25	360
12	300	318.5	321.0	316.0	6.9	53.0	35.6	25	360
14	350	355.6	358.4	352.8	7.9	67.7	45.5	25	360
16	400	406.4	409.7	403.1	7.9	77.6	52.2	25	360
18	450	457.2	460.9	453.5	7.9	87.5	58.8	25	360

Thickness Tolerances: -12.5%